


PLATINUM®
RAIKO




ArcelorMittal
Magnelis®





Magnelis®
Think strategy



Magnelis®

Think strategy

5

- 7 What is Magnelis®?
- 9 Outstanding corrosion performance
 - 11 Corrosion protection mechanism
 - 13 Edge protection with self-healing effect
- 15 Corrosion resistance, accelerated corrosion tests
- 17 Corrosion resistance, proven outdoors
- 19 Cost advantages over competing solutions
- 21 Technical specifications
- 23 Easy to process
- 25 Standards and certification
- 27 The environmentally responsible coating
- 29 Co-engineering Magnelis® solutions

Magnelis®, the best metallic coating through a large panel of markets

- 33 Magnelis® outperforms pre-coated welded tubes
- 35 The durable coating for solar structures
- 41 Optimal protection for agricultural applications
- 45 Construction – Durability guaranteed
- 49 Infrastructure – Durable safety barriers, lighting poles, acoustic walls...
- 51 Industry – Appliances and electrical equipment
- 53 Benefits of Magnelis® in a nutshell



Main advantages



- Excellent corrosion resistance: three times better than galvanised steel (based on outdoor tests)
- Self-healing effect ensures excellent edge protection
- Best and most cost-effective alternative to post-galvanised steels
- Wide feasibility range
- Excellent processing properties
- Environmentally friendly

What is Magnelis®?

Magnelis® is an exceptional metallic coating which provides a breakthrough in corrosion protection. Magnelis® is also the best choice for a wide variety of applications.

Thanks to its unique composition, Magnelis® provides an unprecedented level of surface and cut-edge protection, even in the most hostile environments.

Magnelis® is produced on a classic hot dip galvanising line, but the molten bath has a unique chemical composition including zinc, 3.5% aluminium, and 3% magnesium.



*Magnelis® has a naturally dark grey aspect.
It is available with an environmentally friendly
E-passivation® or it can be oiled on request.*

Magnelis®
provides outstanding
corrosion resistance,
even in harsh
environments




Outstanding corrosion performance

Magnelis® resists corrosion for longer than standard galvanised products and it outperforms coatings containing less magnesium.

The specific composition of Magnelis® (3% Mg and 3.5% Al) is crucial as it leads to a stable and durable layer across the entire surface and edges of the steel. This provides more effective corrosion protection than coatings with a lower magnesium content.

Corrosion resistance in cyclic test for different Zn, Al, Mg compositions



10 µm of coating submitted for an alternated cycling of 8 hours fog cycle (5% NaCl) / dry cycle / humidity cycle
Source: ArcelorMittal R&D



Magnelis® offers
deformed surfaces
extra protection

Corrosion protection mechanism


11

The specific composition of Magnelis® (3% Mg and 3.5% Al) is crucial as it leads to the formation of a very dense, stable, and durable layer of protection. The compact layer of Magnelis® acts as a barrier to corrosion, preventing the underlying steel from coming into contact with the ambient environment. The result is highly effective corrosion protection, even in the harshest environments.

Best protection for deformed areas


Magnelis® will even form a dense layer on highly deformed zones. This gives deformed steel shapes the same protection as flat surfaces. This is a key advantage of Magnelis® compared to other metallic coatings.

Galvanised



Galvanised


Magnelis®



Magnelis®

No red rust observed after 1440 hours of salt spray testing on Magnelis® cup, where the galvanised cup is completely corroded.

The self-healing effect of Magnelis® ensures the protection of uncoated edges, scratches and perforations



The perforated zone on a safety barrier is protected by the self-healing effect of Magnelis®.


Edge protection with self-healing effect

When exposed to the environment, Magnelis® forms a very dense zinc-based protective film, unlike galvanised where the film is very porous.

This unique dense film is also formed on edges, welds, perforations and scratches. In case some red rust was present on these uncoated zones, the red

rust will be gradually covered by the Magnelis® film.

It is almost impossible for the environment to penetrate this film. The result is that Magnelis® provides perfect protection of the whole structure, even on the uncoated edges, scratches and perforations.



Initial exposure period (up to several weeks)*

The exposed cut end of the substrate is oxidised and forms red rust.



Subjected to rain and condensation (beyond several weeks)*

The zinc-based film containing magnesium on the coating layer migrates over the cut end.




Long exposure period (after more than a year)*

Disappearing of red rust and increasing of white rust.



* The speed of the self-healing may depend on the environment.

A woman with dark hair tied back, wearing a white lab coat and safety glasses, is seen from the side, working in a laboratory. She is standing in front of a fume hood, which is emitting a thick cloud of white vapor. The background shows a brick wall and various laboratory pipes and equipment. An orange text box is overlaid on the left side of the image.

The superior corrosion resistance of Magnelis® has been demonstrated in accelerated laboratory testing and proven through outdoor tests

Magnelis® samples are tested in the laboratory.

Corrosion resistance, accelerated corrosion tests

15

Magnelis® versus pre-galvanised
(salt spray test)




Hot dip galvanised 20 µm
after 6 weeks



Magnelis® 20 µm
after 34 weeks


Magnelis® versus post-galvanised
(salt spray test)



Post-galvanised 85 µm
after 12 weeks



Magnelis® 20 µm
after 12 weeks



These are results from a 3CT (VDA 621-415) cyclic corrosion test. Source: ArcelorMittal R&D

Salt spray and cyclic corrosion test results highlighted the superior performance of Magnelis® compared to other metallic coatings.

No red rust was observed on steel with a 20 µm coating of Magnelis® after 34 weeks of salt spray testing. Magnelis® offers a real advantage over post-galvanised steel.

Magnelis® outperforms
galvanised steel in all
types of environments

*Magnelis® samples
at the French Corrosion
Institute in Brest.*

Corrosion resistance, proven outdoors


More than thousand Magnelis® samples have been exposed to a variety of different environments around the world in outdoor tests. The samples included shapes such as flat sheets, tubes, and profiles, and a range of different dimensions.

Every test has confirmed the optimal protection provided by Magnelis® against long-term corrosion.


Magnelis® shows three times better protection than galvanised steel in all types of environments, and even more in very aggressive environments.

Mean yearly consumed thickness* in different environments in microns/year (after 2 years)

Source: ArcelorMittal R&D



Post-galvanised versus Magnelis®



Cost advantages over competing solutions

Advantages over post-galvanised steels

- Freedom to optimise designs thanks to the ability of Magnelis® to protect deformed shapes
- Lower weight of Magnelis® coating (depending on environment) to obtain the same level of corrosion resistance
- Protects flat and deformed surfaces as well as cut edges
- Shortens the logistics chain thanks to simpler fabrication processes.

Cost effective compared to stainless steel and aluminium

- Magnelis® provides the high level corrosion resistance of stainless and aluminium at a significantly lower cost.

Reduces maintenance costs compared to post-painting:

- The use of Magnelis® can avoid the need for post-painting. This leads to cost savings and productivity improvement
- The extended durability of Magnelis® results in reduced maintenance.

Magnelis®
Think strategy




By closely controlling the process conditions, ArcelorMittal is able to ensure the optimal properties of the final product.

Steel thickness can range from 0.45 to 6 mm, while the coating can be from 5 to 35 μm /per side (ZM430).

H240 + ZM

Friction test

Magnelis® offers improved friction behaviour.



Lubrication Oil Fuchs 41075 in excess

Source: ArcelorMittal R&D

Easy to process

Thanks to its highly resistant, adherent metallic layer, Magnelis® can be processed using a variety of methods. These include bending, drawing, and profiling. Magnelis® maintains a high level of corrosion protection, even in the deformed zones.

Outdoor exposure tests have confirmed the exceptional corrosion resistance of Magnelis® on deformed parts compared to galvanised steel. The Magnelis® barrier protects the entire surface including cut edges and perforations.

Powder behaviour comparison

Magnelis® reduces the powdering behaviour.



Lubrication Oil Fuchs 41075 in excess
Source: ArcelorMittal R&D

Formability

Magnelis® proves better results on workability of the product and protection of the processing tools.

Friction tests show that Magnelis® performs better than hot dip galvanised steel.

Steels coated with Magnelis® are easy to process and do not harm processing tools. Magnelis® also enables manufacturers to deform the steel without the need for a lubricant, something that is not possible with galvanised steels.

Weldability

Magnelis® offers improved weldability due to its thinner coating. The process to weld Magnelis® is the same as that used for zinc-coated parts. The same welding consumables, procedures, and guidelines can be used. Arc, spot, and high frequency induction (HFI) welding techniques are all compatible with Magnelis®.

In cases where welded areas need to be re-protected, Magnelis® demonstrates even better corrosion resistance than a post-galvanised coating.

Paintability

Magnelis® can be post-painted and offers superior corrosion resistance compared to other metallic coated steels.



Magnelis® is
the only metallic
coating product
certified for use in
a C5 environment

Standards and certification

Magnelis® has been included in the European standard for hot dip galvanised steel (EN 10346) since July 2015 and Magnelis® is expected to be included in the near future in the ASTM.

The excellent corrosion resistance of Magnelis® has seen it certified for use by external bodies including: CSTB (France), DIBt (Germany), SP (Sweden).

Magnelis® is the only metallic coating product certified for use in a C5 environment by the SP certification body in Sweden. It has also been included in the highest corrosion resistance class (KIII) by DIBt in Germany.

Magnelis® is suitable for food contact applications in accordance with European regulation EC 1935/2004.

Magnelis® complies with the European directives covering:

- Restriction of Hazardous Substances (RoHS)
- Registration, evaluation, authorisation and restriction of chemicals (REACH)
- Waste Electrical and Electronic Equipment (WEEE)

CSTB
At future en construction

ENVELOPPE ET REVÊTEMENTS
Constructions Légères et Couvertures

Evaluation Technique Préaleable de Matériau

Barage et Couverture
métallique

Ce rapport n'a pas valeur d'avis
technique au sens de l'article 21
de la loi 2012-29 du 12 février 2012
relatif à l'usage des Groupes Spéciaux
d'Experts Techniciens et est le
résultat des demandes d'avis Tech-
niques sur des ouvrages de cou-
vertures, barages et façades dont les
titres sont consultés avec le respec-
tueux.

Il a été établi en collaboration avec
des experts de la corrosion et des
spécialistes des façades et cou-
vertures métalliques.

Revêtement métallique sur tôle d'acier

Magnelis®

Titulaire : ArcelorMittal
23 rue de la Basse Saint-Jean
86-4000 LIGNE
Belgique

Distributeur : ArcelorMittal
23 rue de la Basse Saint-Jean
86-4000 LIGNE
Belgique

Vendeur : ArcelorMittal Europe
32 Chemin de la Kurnel
86-4400 VIEUX-BAUMET
Belgique

Commission chargée de formuler des Avis
Techniques n° 2

Constructions, Façades et Cloisons Légères

Séance du 22 novembre 2011
Vu pour enregistrement le 18 JUIN 2012

Cette Evaluation Technique comporte 8 pages. Sa reproduction n'est autorisée que sous la forme de fac-similé ou
intégral et sans aucun parti-pris de CSTB.

Sous-traité de la coordination des Arts Techniques
CSTB, 88 rue de la Basse Saint-Jean, 86-37447 Mors-la-Vallée Cedex 2
Tél. : 02 84 88 82 82 - Fax : 02 84 88 79 37 - Internet : www.cstb.fr
© CSTB 2012

Allgemeine bauaufsichtliche Zulassung

Zulassungsnummer:
Z-30.11-01

Antragsteller:
ArcelorMittal
19 Avenue de la Liberté
2000 LUXEMBOURG
LUXEMBOURG

Zulassungsgegenstand:
III dem Beschichtungssysteme Magnelis korrosionsschutzfähige Stahlbänder (Coils) für die
Herstellung dinnwandiger kaltgeformter Bauteile

Deutsches
Institut
für
Bautechnik

Zulassungsstelle für Bauelemente und Bauteile
Bautechnisches Prüfamt
Eine vom Bund und den Ländern
gemeinsam getragene Anstalt des öffentlichen Rechts
eingetragen im VZStB, der GStB und der VZStB

Datum: 23.07.2013 Geschäftsbereich: 136-1.30.11-1210

Gültigkeitsdauer:
vom 23. Juli 2013
bis 23. Juli 2018



Swedish Technical Approval SC0559-13

and decision on production control, in accordance with chapter 8, 22 and 23 §§ Planning- and
Building Act (2010:900), PBL.

Magnelis ZM310, Corrosion protection coating

Holder
ArcelorMittal Global Research & Development, C / Chavarrí 6, 48910 Sestao, Biscaya, Spain
VAT number: ES 820431300
Internet: www.arcelormittal.com

Information supplied by
ArcelorMittal Global Research & Development, Rue de la Digue, 22, BE-4400 Nieuwste, Belgium
Tel.: +32 4 236 21 99, E-mail: corrosion.dtu@arcelormittal.com

Product
Corrosion protection coating, Magnelis ZM310, is a special coating composed by an alloy of zinc,
aluminum and magnesium. Coating thickness 25 µm per side.

Intended use
Intended as corrosion protection of steel sheet for indoor- and outdoor applications. The
corrosion protection is suitable for corrosivity class C5, according to ISO 12944-2
described class, based on a deemed expected lifetime of 15 years.

Trade name
Magnelis ZM310

Approval
The product satisfy the requirements set forth in chapter 8, 4 § 1 PBL, in respect to and under
conditions stated in this certificate, and are therefore approved in accordance with the
provisions of the following sections of the Swedish mandatory provisions on application of the
European construction standards (Eurocodes), (EKS) issued by the National Board of Housing,
Building and Planning:

EKS

Durability

Durability

Section A, 7 §

Section E, EN 1993-1-1, clause 2.1.3

Associated documents

-

Control

Production control is to be performed in accordance with instructions described in control

In production and during its service life, Magnelis® has a significant lower environmental impact compared to its competitors




The environmentally responsible coating

The application of a Magnelis® coating ensures the preservation of natural resources as it uses significantly less zinc than pure zinc coatings. Magnelis® also reduces zinc runoff* to soils.

Magnelis® is 100% recyclable and does not contain any harmful elements. It is REACH compliant and an environmental product declaration (EPD) is available.

Zinc runoff rate*

Magnelis® considerably reduces zinc runoff into soil.




* the rate of dissolution of a material from its surface into the soil

Source: French Corrosion Institute

The production of Magnelis® also has a lower environmental impact compared to other highly durable materials such as stainless steel or aluminium.

Production impact on CO₂ emissions

CO₂ emissions for the production of Magnelis® are much lower than for aluminium, a difference that is not compensated by aluminium during the use phase, even when aluminium parts are lighter than steel parts.



Sources: ArcelorMittal R&D; European Aluminium Association, World Steel Association, Eurofer



Our support can help
you to optimise the
use of Magnelis®


Co-engineering Magnelis® solutions


ArcelorMittal is offering an innovative co-engineering approach to its customers in order to optimise the use of Magnelis® and to achieve the best possible results and cost reduction.


Our co-engineering team includes researchers and technicians with a strong background in mechanical design.

ArcelorMittal's assistance to customers can be applied at all stages of product development, from initial design through to serial production. We can help you to take every advantage of the benefits Magnelis® can offer:

- The most suitable steel grade and coating for your application
- Cost optimisation through thickness reduction and process improvements (using finite element simulations)
- Improving the quality and durability of your product
- Definition of minimal mechanical properties and thicknesses for successful production
- Deformation analysis of stamped parts to validate the theoretical analysis
- Technical support during production.








Magnelis[®], the best metallic coating through a large panel of markets

31

- 33 ■ Magnelis[®] outperforms pre-coated welded tubes
- 35 ■ The durable coating for solar structures
- 41 ■ Optimal protection for agricultural applications
- 45 ■ Construction – Durability guaranteed
- 49 ■ Infrastructure – Durable safety barriers, lighting poles, acoustic walls...
- 51 ■ Industry – Appliances and electrical equipment

A close-up photograph of a metal profile, likely a C-channel, showing a weld joint. The top flange is coated with a dark blue material, while the main body is a lighter, metallic silver color. The weld joint is visible on the right side, showing a textured, fused surface. The background is a plain, light-colored surface.

Magnelis® provides
a higher level of
protection on welded
areas compared to
other coatings

Magnelis® outperforms pre-coated welded tubes

33

tubes

Magnelis® has very clear advantages when it comes to tubes. On a standard galvanised tube, the welded area is the weak point for corrosion. Magnelis® increases the protection and lifetime of the welded zone to unprecedented levels.

Processing

Magnelis® offers similar weldability to standard hot dip galvanised steel. The same welding consumables, procedures, and guidelines can be used for structural tubes and pipes. Arc welding, spot welding, and high frequency induction (HFI) welding are all compatible with Magnelis®.

Self-healing effect

Magnelis® self-heals on cut edges and thin welded zones. The zone is progressively covered with protective Magnelis® compounds which act as a barrier to corrosion. The result is outstanding corrosion resistance, even on welded zones.

The life of a welded tube can be extended significantly beyond that of a post-galvanised tube if the welded area is re-protected with Magnelis®.

Magnelis® versus pre-galvanised



Magnelis® ZM120
welded,
not re-protected

Galvanised Z275
welded,
not re-protected

Magnelis® versus post-galvanised



Magnelis® ZM310
welded and
re-protected

Post-galvanised
welded

cyclic test 3CT (VDA 621-415) after 33 weeks of tests



The durable coating for solar structures

Magnelis® supports moves to generate clean and renewable energy by offering advanced corrosion protection for solar installations. Magnelis® is the preferred coating solution for both concentrating solar power (CSP) plants and ground-mounted structural solutions for photovoltaic (PV) solar farms. It offers increased durability, the best possible protection against corrosion and abrasion.

Magnelis® extends the life of solar structures so operators can maximise the return on their investment. Its key advantages in these applications are:

- Guaranteed durability up to 25 years
- Improved resistance against abrasion
- Effective against corrosion even placed in soil
- Large feasibility range both in thickness and steel grade
- Cost effective
- Rapid installation
- Reduces environmental impact.

The minimum recommended coating for the upper parts of solar structures is Magnelis® ZM310 at 25 µm per side. For areas in soil or subject to higher abrasion, we recommend Magnelis® ZM430 at 35 µm per side.

Magnelis® can be supplied in a wide range of steel grades and thicknesses up to 6 mm. This flexibility allows operators to optimise the design and total cost of their solar structures.



A 25-year guarantee* is available for Magnelis® ZM310 used in the support structures of solar applications. It is the first metallic coating to be guaranteed in marine conditions (C5-M, ISO 12944-2).

* Guarantee for Magnelis® ZM310 is subject to project-specific conditions. Contact us for more information.

Magnelis® is
the preferred material
for the structural
components
of solar fields



Optimum abrasion resistance for steel solar structures in deserts

37

solar

Magnelis® has much higher hardness compared to standard zinc coatings. This has a direct and positive impact on the abrasive wear resistance of the coating.


The hardness of Magnelis® is much higher than that of hot dip galvanised coatings, increasing its resistance to abrasion

Galvanised		64
Magnelis®		141

Hardness Vickers (HV)


The excellent abrasion resistance of Magnelis® has been proven through outdoor exposure tests in desert environments.

Magnelis® performs much better than galvanised steels in sandy environments



Mean coating consumption/year ($\mu\text{m}/\text{year}$)
(four/two years outdoor exposure in Dubai)
Source: French Corrosion Institute





The very dense film
of Magnelis® assures
the best possible corrosion
protection in soil

Magnelis[®], superior behaviour in soils


39

solar

When it comes into contact with soils, Magnelis[®] also produces its protective film to cover the steel surface. This very dense film reduces the contact between the steel and the soil, dramatically slowing the progression of corrosion.

Magnelis[®] ZM430 is the preferred corrosion protection for steel structures which are placed in soil.

Comparison of corrosion rates for galvanised, post-galvanised, and Magnelis[®] coated steels during one year in soil.







Optimal protection for **agricultural** applications

Magnelis® is used in a variety of agricultural applications due to its excellent corrosion resistance in highly alkaline atmospheres (pH between 10 and 13) and those rich in ammonia.

Vineyards

Magnelis® ensures ultimate corrosion protection for vineyard poles. Poles coated with Magnelis® have a life span in line with that of the vines they support.

Poles account for more than 60% of the cost of vineyard fences. Magnelis® poles are at least 20% more cost-effective than wood and galvanised poles and can perform over the total lifetime of the vines.

Outdoor tests have proven that Magnelis® has superior corrosion resistance in soils compared to zinc-heavy coatings. Magnelis® is more stable than conventional coatings when it is placed in contact with soil.

Magnelis® is eco-friendly and reduces zinc runoff to soil considerably compared to post-galvanised products.

Greenhouses

Greenhouse structures must sustain extremely warm and humid atmospheres. Magnelis® offers excellent corrosion resistance in this application due to its very dense protective layer.

In addition to its excellent formability, Magnelis® also provides a high level of corrosion resistance on deformed parts.



Optimal protection for agricultural applications


43

Animal housing

Farm buildings housing cattle, pigs, and poultry face severe challenges from atmospheric corrosion. Magnelis® coated profiles and tubes are the ideal answer to guarantee the durability of these structures. Multiple tests (including accelerated tests and long exposure on real farms) have demonstrated the outstanding corrosion performance of Magnelis® in animal housing. Magnelis® reduces the risk of corrosion and disease as bacteria have no corrosive areas in which to hide.

Thanks to its high surface hardness Magnelis® is also better at resisting animal scratches. Magnelis® also eliminates the need for post-painting, and can replace stainless steel or aluminium.

Magnelis® is available in all dimensions required for animal housing, and offers a very cost-effective solution.



Measurement of mass loss:
pH: 11.7 – Solution with 5% NH₃ –
T: 20°C – Test duration 24 h

Source: ArcelorMittal R&D

Silos

Magnelis® offers excellent outdoor corrosion protection for silos, wherever they are located. The hard surface of Magnelis® also reduces the abrasive effect of grain on the coating.

Magnelis® is suitable for food contact applications such as the interiors of fermentation silos and meets the requirements of European regulation EC 1935/2004.

Magnelis® is available in thicknesses ranging from 0.45 to 6 mm, and in various steel grades, coating weights, and levels of protection.



Magnelis® guarantees
a cost effective and
long life solution



Construction

Durability guaranteed

45

construction

The remarkable corrosion resistance of Magnelis® allows it to be used for a wide range of structural applications. These include the sub-structures of ventilated facades, composite floors, purlins for roofs, side rails for walls, rainwater systems, and light steel framing. But it can also be used for roof and wall profiles in some corrosive environments such as coastal areas, agricultural structures, and water transport systems.

Longer lifetime

Magnelis® increases the lifetime of structures by a factor of three compared to hot dip galvanised solutions. In more severe environments, the benefits of Magnelis® can be even greater.

Self-healing effect

When cut, perforated, or scratched, Magnelis® slows down corrosion by forming a very dense zinc-based protective film. This ensures perfect protection of the whole structure.

Excellent workability

Profiling processes are facilitated by the excellent forming behaviour of Magnelis® as it has a lower friction coefficient than galvanised steel. The Magnelis® coating also adheres firmly to the steel to prevent powdering during processing.

Reduced coating thickness

The superior corrosion protection of Magnelis® offers our customers two possibilities. They can increase the level of corrosion protection with the same metallic coating thickness; or they can achieve the same protection while significantly reducing coating thickness.

Low total cost of ownership

Magnelis® offers significant cost reductions as it reduces the need for ongoing maintenance and avoids the need for additional painting. This makes Magnelis® the most cost-effective solution compared to galvanised and post-galvanised corrosion protection.

Contact with concrete

As concrete hardens, a very alkaline environment is created. This can be extremely aggressive against coated steel. Magnelis® resists corrosion in these applications much better, and is the preferred metallic coating for applications which come into contact with concrete.

Wide feasibility range

Magnelis® is available in a wide range of high strength steels, allowing design optimisation.



Construction

Diverse range of applications

47

construction

Building structures

Magnelis® is the perfect corrosion protection solution for roof structures and purlins, wall side rails, facade sub-structures, and light steel-framed structures. It can be utilised in outdoor, exposed, semi-exposed, or unexposed environments to ensure a longer lifetime than hot dip galvanised steel and other traditional coatings. The performance of Magnelis® has been proven in outdoor tests.


Rainwater and roofing systems

Magnelis® can be utilised for roofs and corrugated profiles in aggressive environments such as marine or agricultural areas. It is the first metallic coating steel to be classified for use in a C5 environment and comes with a guarantee up to 20-years. In non-marine environments, the guarantee can be up to 25-years. When used in rainwater systems, a 10-year guarantee is available.

Flooring

Composite floor systems made with steel and concrete are flexible and adaptable to any kind of structure or renovation. They allow large spans and reduce floor thickness while maximising interior space.

Metallic coated steel with Magnelis® is the ideal solution for durable, long lasting composite floors. It offers excellent corrosion performance when in contact with concrete or in high alkaline atmospheres.



Magnelis® is the only metallic coating with a 20-year guarantee for roofing and in marine environments (C5-M more than 300 m from the sea). A guarantee of up to 25 years can be provided for inland roofing applications.



Infrastructure

Durable safety barriers, lighting poles, acoustic walls...

49

infrastructure

Magnelis® is widely used to protect safety barriers, lighting poles, road signs, acoustic walls, bridge parapets, and many other infrastructure applications.

Outstanding corrosion protection

The excellent corrosion behaviour of Magnelis® has been extensively proven in outdoor tests. Magnelis® outperforms galvanised steel by a factor of three, and higher in more severe environments.

Self-healing effect

Magnelis® offers protection for cut edges and perforations thanks to its inbuilt self-healing properties.

Reduced corrosion in soil

Outdoor tests have proven that Magnelis® has superior corrosion resistance in soils compared to zinc-heavy coatings. Magnelis® is more stable than conventional coatings when it is buried in the soil and results in less zinc runoff. Magnelis® ZM430 offers the best possible corrosion protection in soil.

Wide feasibility range

Magnelis® can be provided in a range of thicknesses and grades suitable for road safety and other infrastructure applications.

Cost competitive compared to post-galvanisation

Using Magnelis® for infrastructure applications offers clear cost advantages. Total cost of ownership is optimised as production, logistic, installation, and maintenance costs are reduced significantly.



ArcelorMittal offers a guarantee of up to 20-years on Magnelis® in road safety applications.

Magnelis® is now included in the EN 10346 standard for continuously hot dip coated steel flat products, and the EN 1317 standard for road safety systems. Magnelis® solutions have also been certified by bodies which oversee the Construction Product Regulation. Certifications have been granted in Austria, Belgium, the Czech Republic, Norway, and Spain. Certification is ongoing in other countries.



Industry

Appliances and electrical equipment

51

industry

Manufacturers of appliances and electrical equipment are requesting significantly improved corrosion protection, while maintaining processing and cost effectiveness. Magnelis® is the answer to these demands. Magnelis® is already widely used for the casings, structures, and hinges of appliance units, cable trays, and cooling towers.

Outstanding corrosion protection

The excellent corrosion behaviour of Magnelis® has been proven through extensive outdoor tests. Magnelis® outperforms galvanised steel by a factor three.

Self-healing effect

Magnelis® also protects edges and perforations thanks to its inbuilt self-healing properties.

Significantly improved protection against white rust

Conventionally galvanised steel shows substantial signs of white rust after a salt spray test. Magnelis® offers a huge improvement in white rust resistance. Salt spray tests have shown it lasts much longer.

Reduced coating thickness

The superior corrosion protection of Magnelis® offers our customers two possibilities. They can increase corrosion protection by applying the same coating thickness, or target the same level of protection with a significantly thinner metallic coating layer.


Scratch resistance

Thanks to its very high hardness, Magnelis® offers excellent wear and abrasion resistance.

Improved productivity and paintability

The lower friction coefficient and improved adhesion of Magnelis® increases its processing properties. The easiness to post paint Magnelis® can bring a further improvement of corrosion resistance versus galvanised steel.

Magnelis® ensures corrosion resistance while maintaining the electrical conductivity of cable trays.



Benefits of **Magnelis®** in a nutshell

Features		Magnelis® versus hot dip galvanised (Zn)
Anti-corrosion properties	Outdoor corrosion	+++
	Agricultural buildings (animal housing, barns, greenhouses, silos...)	+++
	Marine environments (construction, swimming pools...)	+++
	Industrial environments (acid- or alkaline-rich environments)	+
	High humidity	+++
	Contact with concrete	+++
	Abrasion	+++
	Soil corrosion	+++
	Edge protection thanks to self-healing effect	+++
	Perforations or scratches on exposed applications	+++
	Corrosion of formed parts (bent or stamped)	+++
	Temporary protection (transport, storage)	+++
Processing properties	Bending and profiling	+
	Forming and shaping	+
	Welding (equivalent coating thickness)	=
	Painting	++

Credits

cover	Movemedias
page 2	Jeroen op de Beeck
page 4	Kurp Dach
page 6	Jeroen op de Beeck
page 7	Philippe Vandenameele
page 8	Jeroen op de Beeck
page 10	Jeroen op de Beeck
page 12	© Shutterstock – Robsonphoto, Grupo Condesa
page 14	ArcelorMittal
page 16	French Corrosion Institute
page 18	Jeroen op de Beeck
page 20	ArcelorMittal
page 22	Kurp Dach
page 24	Jeroen op de Beeck
page 26	French Corrosion Institute
page 28-29	ArcelorMittal R&D
page 30	Metpol
page 32	Jeroen op de Beeck
page 34	CWF
page 36	© Shutterstock – Tom Grundy
page 38	Profil du Futur
page 40	© Shutterstock – Image HOUSE
page 42	Altuntas
page 44	beSteel
page 46	Metro Station Albrook, Panama – Contractor: Aceros Estrella
page 48	© Shutterstock – feiyuezhangjie
page 50	© Shutterstock – maxuser
page 52	Perforated Sheet – Didier Bridoux

Copyright

All rights reserved. No part of this publication may be reproduced in any form or by any means whatsoever, without prior written permission from ArcelorMittal. Care has been taken to ensure that the information in this publication is accurate, but this information is not contractual. Therefore ArcelorMittal and any other ArcelorMittal Group company do not accept any liability for errors or omissions or any information that is found to be misleading. As this document may be subject to change at any time, please consult the latest information in the product document centre at industry.arcelormittal.com

Magnelis®
Think strategy

ArcelorMittal Europe – Flat Products

24-26, boulevard d'Avranches

L-1160 Luxembourg

industry.arcelormittal.com/magnelis

